

Superiorseal 2 Pack *Gloss and Matt*

Description

Superiorseal 2 Pack when cured forms a durable and chemically resistant surface ideal for use as a replacement for Epoxy coatings especially on concrete garage floors.

Features and Benefits

- Excellent for Interior and Exterior use
- Topical/Film forming - Available in gloss or matt finish
- Hard wearing surface
- Provides a dust free surface
- Excellent on concrete, brick and pavers.
- Hot tyre resistant

Properties

Product Number	Gloss Part A – M573 & M574 Matt Part A – M576 & M577 Part B – M578 & M579	
Appearance	Part A – Milky white liquid Part B – Clear liquid	
System	Two Pack Urethane	
Odour	Mild	
Solids Volume	Part A – 33-35% Part B – 73-77% Total – 41-43%	
Dry Film Clarity	Excellent – Not tinted	
Specific Gravity	Part A – 1.0 Part B – 1.15	
VOC Content	98 g/L	
Flammability	Non-Flammable	
Pot Life	3-4 Hours	
Dry Time	10-15 Minutes	
Recoat Time	40-60 Minutes	
Curing Time	72 Hours	
UV Resistance	Excellent	
Resistances	Oil Solvent Stain	Salt Water



Superiorseal 2 Pack *Gloss and Matt*

Application

Preparation

- Do not apply if rain is imminent
- Surface must be free from dust, oil and grease prior to application
- Do not apply if temperatures are less than 10 °C or greater than 30 °C
- Protect adjacent areas by masking to avoid splashes or overspray onto surfaces not intended to be treated

Coating

- Mix well before use
- Stir 4 Parts of 'A' with 1 Part of 'B' for 2-5 minutes using a drill/paint mixer until consistent and allow 10-20 minutes for aeration to dissipate.
- Apply with a roller (Lambswool, Mohair or Microfiber) or low-pressure spray for a 30 µm thick coat
- Overapplying matt coating will lead to glossier finish
- Allow 40-60 minutes to dry prior to applying second coat

Clean Up

Clean any tools used in the application process with water immediately after use.

Storage

Store in a well-ventilated cool location between 10 °C and 30 °C.

Keep sealed when not in use.

Coating Maintenance

Rinse surface regularly with water to remove contaminants. Degreasers and cleaners can be used for the removal of stains.

Packaging

Volume (L)	Container
5	Jerry
20	Cube

Coverage

	Uncoated Concrete (m ² /L)	Pre-Coated Concrete (m ² /L)
First Coat	6-8	10-12
Second Coat	10-12	10-12

Note: Subject to colour and condition of surface a third coat may be required to reach desired result.

Safety

Always wear appropriate PPE while handling product.

Please Note: This information is based on current knowledge. It does not constitute a guarantee and we recommend that testing should be undertaken to ensure that the final result is satisfactory for the intended application. The quality of the product is guaranteed under our General Conditions of Sale.

